

Appln No. 09/308,607

Amdt date February 17, 2004

Reply to Office action of October 14, 2003

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Currently Amended) A process for producing porous spherically-shaped bio-ceramics comprising dropping a starting material for ceramics into a low temperature medium from a thin tube having an inner diameter ranging from about 0.3 to 2 mm, followed by freeze drying in the medium and then sintering the same, wherein the starting material is obtained by adding, to a calcium phosphate in the form of a powder having a size of not more than 100 μm , a 3 to 15% by weight aqueous solution of a binder in an amount of 2 to 4 times the weight of the powder.

2. (Previously Presented) A process for producing porous spherically-shaped bio-ceramics as claimed in claim 1, wherein the calcium phosphate is hydroxyapatite, tricalcium phosphate, calcium dihydrogenphosphate, tetracalcium phosphate, octacalcium phosphate, or a mixture thereof.

3. (Previously Presented) A sustained drug release product obtained by forming the porous spherical-shape bio-ceramics obtained according to claim 1 or 2, wherein the pores are impregnated with a drug.

4. (Previously Presented) A sustained drug release product as claimed in claim 3, wherein, after the drug is

Appln No. 09/308,607

Amdt date February 17, 2004

Reply to Office action of October 14, 2003

impregnated into the porous bio-ceramics, the impregnated parts are plugged by said bio-ceramics, whereby the sustained release time of the drug is controlled.

5. (Currently Amended) A process for producing porous spherically-shaped bio-ceramics comprising:

bringing a starting material for bio-ceramics into contact with a low temperature medium by dropping the starting material into the low temperature medium from a thin tube having an inner diameter ranging from about 0.3 to 2 mm, wherein the starting material is obtained by adding, to a calcium phosphate in the form of a powder having a size of not more than 100 μ m, a 3 to 15% by weight aqueous solution of a binder in an amount of 2 to 4 times the weight of the powder, followed by freeze drying in the medium to form a freeze dried product and;

thereafter sintering the resultant freeze dried product.

6. to 10. (Cancelled)

6 11. (Previously Presented) A process for producing porous spherically-shaped bio-ceramics as claimed in claim 5, wherein the calcium phosphate is hydroxyapatite, tricalcium phosphate, calcium dihydrogenphosphate, tetracalcium phosphate, octacalcium phosphate, or a mixture thereof.

7 12. (Previously Presented) A process for producing a sustained drug release product comprising impregnating the pores

Appln No. 09/308,607

Amdt date February 17, 2004

Reply to Office action of October 14, 2003

of the porous spherical-shape bio-ceramics obtained according to claim 1 or 2 with a drug.

8 ~~13~~. (Previously Presented) A process as claimed in claim 12, wherein, after the drug is impregnated into the porous bio-ceramics, the impregnated parts are plugged by said bio-ceramics, whereby the sustained release time of the drug is controlled.

9 ~~14~~. (Previously Presented) A process as claimed in claim 1, wherein the binder slurry is an aqueous solution of one or more of a water-soluble cellulose derivative, polyvinyl alcohol, polyacrylic acid, polyacrylamide, polyvinyl pyrrolidone, polyethylene glycol, and starch.

15. (Cancelled)

10 ~~16~~. (Previously Presented) A filler for regenerating body tissue comprising porous spherically-shaped bio-ceramics obtained by a process according to claim 1.

11 ~~17~~. (Previously Presented) A method for regenerating body tissue comprising introducing into areas where body regeneration is desired porous spherically-shaped bio-ceramics obtained by a process according to claim 1.

12 ~~18~~. (Previously Presented) A process for producing porous spherically-shaped bio-ceramics as claimed in claim 1, wherein

Appln No. 09/308,607

Amdt date February 17, 2004

Reply to Office action of October 14, 2003

the porous spherically-shaped bio-ceramics each have a diameter ranging from about 0.01 to about 10 mm.

- 13 19. (New) A process for producing a sustained drug release product according to claim 1 or 5 wherein the low temperature medium is liquid nitrogen.

Appln No. 09/308,607

Amdt date February 17, 2004

Reply to Office action of October 14, 2003

Amendments to the Specification

Please amend the specification by inserting the following replacement paragraphs.

Please replace the paragraph beginning at page 12, line 35 with the following replacement paragraph:

1 g of calcium phosphate powder (#400 mesh or less) having Ca/P = 1.48 synthesized by a known wet synthesis method was mixed into 3 g of a 10% by weight aqueous solution of polyvinyl alcohol, then 0.5 g of ion exchange water was added and the mixture further mixed and stirred. 10 ml of the slurry obtained was filled into a thermosyringe and a 24G needle (inner diameter 0.47 mm) was used to drop it into liquid nitrogen. The frozen product obtained was dried using a vacuum freeze dryer, then was sintered at 1400°C for 5 hours to obtain 0.9 g of spherical-shape ceramics. The spherical-shape frozen product ~~ceramics~~ obtained has a diameter of 0.8 to 1.2 mm. Powder X-ray measurement confirmed that the spherical-shape ceramics was a single phase of α -tricalcium phosphate.

Please replace the paragraph beginning at page 14, line 25 with the following replacement paragraph:

1 g of calcium phosphate powder (#400 mesh or less) having Ca/P = 1.48 synthesized by a known wet synthesis method was mixed into 3 g of a 10% by weight aqueous solution of

Appln No. 09/308,607

Amdt date February 17, 2004

Reply to Office action of October 14, 2003

polyvinyl alcohol, then 0.5 g of ion exchange water was added and the mixture further mixed and stirred. 10 ml of the slurry obtained was filled into a thermosyringe and a 24G needle (inner diameter 0.47 mm) was used to drop it into liquid nitrogen. The frozen product obtained was dried using a vacuum freeze dryer, then was sintered at 1400°C for 5 hours to obtain 0.9 g of spherical-shape ceramics. The spherical-shape frozen product ~~ceramics~~ obtained has a diameter of 0.8 to 1.2 mm. (See Figs. 6(a) and 6(b).)